

THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

5

LISTING OF CLAIMS

1. (Previously Presented) A print medium comprising:

an ink-receiving layer and a coated, absorptive paperbase selected from the group consisting of coated, calendered paper; coated, uncalendered paper and cast coated paper; the ink-receiving layer being present on the
10 coated paperbase from about 3 grams per square meter to about 7 grams per square meter, and the coated paperbase having a Sheffield smoothness less than approximately 20 and a Sheffield porosity less than approximately 10.

15

2. (Previously Presented) The print medium of claim 1, wherein the ink-receiving layer is present from approximately 4 grams per square meter to approximately 6 grams per square meter.

3. (Original) The print medium of claim 1, wherein the ink-receiving
20 layer comprises at least one water-soluble polymer, a cross-linking agent, a mordant, inorganic particles, and at least one surfactant.

4. (Original) The print medium of claim 3, wherein the at least one water-soluble polymer comprises at least one polyvinyl alcohol; the cross-linking
25 agent comprises boric acid; the mordant comprises a least one of diallyldi-

methyl-ammonium chloride, a cationic latex, or aluminum triformate; and the inorganic particles comprise cationic, superfine colloidal silica.

5. (Canceled)

5

6. (Previously Presented) The print medium of claim 3, wherein the at least one surfactant comprises at least one nonionic, organosilicone surfactant.

10

7. (Previously Presented) The print medium of claim 3, wherein the at least one surfactant is at least one polysiloxane-polyethylene oxide compound or at least one polysiloxane-polyethylene oxide polypropylene oxide compound.

15

8. (Canceled)

9. (Withdrawn—currently amended) A method of forming a print medium having improved image quality and permanence, comprising:

providing a coated paperbase selected from the group consisting of coated, calendered paper; coated, uncalendered paper and cast coated paper; and

20

applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter, the coated paperbase having a Sheffield smoothness less than approximately 20 and a Sheffield porosity less than approximately 10.

25

10. (Canceled)

11. (Withdrawn) The method of claim 9, wherein applying an ink-
5 receiving layer to the coated paperbase at less than approximately 10 grams
per square meter comprises applying the ink-receiving layer from approxi-
mately 3 grams per square meter to approximately 7 grams per square meter.

12. (Withdrawn) The method of claim 9, wherein applying an ink-
10 receiving layer to the coated paperbase at less than approximately 10 grams
per square meter comprises applying a coating composition comprising at
least one water-soluble polymer, a cross-linking agent, a mordant, inorganic
particles, and at least one surfactant.

13. (Withdrawn) The method of claim 12, wherein applying an ink-
15 receiving layer to the coated paperbase at less than approximately 10 grams
per square meter comprises applying a coating composition comprising at
least one polyvinyl alcohol; boric acid; at least one of diallyldimethylammo-
nium chloride, a cationic latex, or aluminum triformate; cationic superfine col-
20 loidal silica; and at least one polysiloxane-polyethylene oxide compound.

14. (Withdrawn) The method of claim 12, wherein applying an ink-
receiving layer to the coated paperbase at less than approximately 10 grams
per square meter comprises applying the ink-receiving layer from approxi-
25 mately 4 grams per square meter to approximately 6 grams per square meter.

15. (Withdrawn) The method of claim 9, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter comprises coating the ink-receiving layer on the coated paperbase at less than approximately 10 grams per square meter.

16. (Withdrawn—currently amended) A method of printing an image having improved image quality and permanence, comprising:
providing a print medium comprising
a coated paperbase selected from the group consisting of coated, calendered paper; coated, uncalendered paper and cast coated paper;
and an ink-receiving layer present on the coated paperbase at less than approximately 10 grams per square meter, the coated paperbase having a Sheffield smoothness less than approximately 20 and a Sheffield porosity less than approximately 10; and
printing the image on the print medium.

17. (Canceled)

18. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on the coated paperbase at less than approximately 10 grams per square meter comprises providing the ink-receiving layer on the coated paperbase from approximately 3 grams per square meter to approximately 7 grams per square meter.

19. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on the coated paperbase at less than approximately 10 grams per square meter
5 comprises providing the ink-receiving layer comprising at least one water-soluble polymer, a cross-linking agent, a mordant, inorganic particles, and at least one surfactant.

20. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on
10 the coated paperbase at less than approximately 10 grams per square meter comprises providing the ink-receiving layer comprising at least one polyvinyl alcohol; boric acid; at least one of diallyldimethylammonium chloride, a cationic latex, or aluminum triformate; cationic, superfine colloidal silica; and at
15 least one polysiloxane-polyethylene oxide compound.